



16-0201 Ankolux Aqua Base Stain VC/D

- Version 220623 : water-borne translucent wood-stain for exterior and interior use.
- Composition : based on waterborne alkyd-emulsion
- Typical characteristics :
- very good penetration into wood
- good resistance to UV radiation
- good adhesion on bare wood
- Recommended uses : as a weather resisting, translucent low-film building wood-stain for dimensionally non-stable wood components. Or as a penetrating first coat followed by Ankolux Woodstain TP or Woodcoat TP.
- Color(s) : standard translucent wood colors.

Technical specifications (20°C and 65% R.H.)

- Solid content : approx. 15 (by volume)
- Density : approx. 1,01 gr/cm³
- Viscosity : approx. 25-35 seconds DIN cup 4
- Gloss : matt to eggshell depending on penetration
- Drying :
- dustdry : approx. 1 hour
- recoatable : approx. 1 hours

* N.B. drying speed/performance is very much dependent of temperature, humidity and particalary air speed circulation!

- Thinner : do not thin
- Application : brush, spray (cup) for horizontal treatment, dipping
- Cleaning tools : hot water, soap



| | |
|--------------------------|--|
| Practical spreading rate | : dependent of the open-wood structure. Fine sawn: 7-11 m ² /ltr Smooth sawn: 11-14 m ² /ltr |
| Application conditions | : do not use at an ambient and object temperature below 8°C and a maximum R.H. of 85%. |
| Storage | : cool and frost-proof, the quality of the product should not deteriorate during the storage. |
| Shelf life | : minimal 6 months in unopened tin. Stir well before use. |
| Special note | : for more information, see the safety data sheet of this product. |

Disclaimer

The information given in this technical data sheet is only a general product description, based on our experiences and tests and therefore does not represent a specific practical case. Consequently Anker Stuy Verven doesn't guarantee the functionality or result and takes no responsibility in this respect. We advise our clients to test the applicability of the product to the nature and the state of the surfaces and to carry out the necessary representative tests in case of doubt. Please contact our R&D department as the occasion arises. Attention: our clients should verify whether the present technical data sheet hasn't been replaced by a more recent version.

